



DIAMOND POLYMERS, INC.

## High Impact ASA Weatherable Polymer

Sheet Extrusion Grade

# Diamaloy GLY 7010

Diamaloy GLY 7010 resin is a high-gloss, high impact grade of ASA (acrylonitrile-styrene-acrylate) with good resistance to weather aging. It has good melt strength for extrusion and thermoforming, and it can be easily coextruded.

### Applications

Typical applications include those requiring weatherability and high impact such as in pool and spa applications. As with any product, use of Diamaloy GLY 7010 resin in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

### Weatherability

Diamaloy GLY 7010 exhibits good resistance to weather aging in unpainted outdoor applications. Color changes may occur in certain colors but are minimal in comparison with ABS (acrylonitrile butadiene styrene) under similar exposure conditions. For optimum performance, appropriate pigments should be used. In coextrusion applications, Diamaloy GLY 7010 offers UV (ultraviolet) protection only if the cap layer is at least 15 mils thick after thermoforming. In most cases, this requires at least a 20% Diamaloy GLY 7010 cap. Since weatherability is dependent on certain variables, such as resin color, end-use environment, and length of exposure, users need to determine whether color, appearance, and property shifts are acceptable for their intended applications. Please consult your DIAMOND POLYMERS ASA representative for further information.

### Drying

Drying prior to processing is recommended in a desiccant dehumidifying hopper dryer. An inlet air dew point of -20°F (-29°C) or below is recommended to achieve a moisture content of  $\leq 0.04\%$ . Typical drying conditions are 3-4 hours at 180° - 190°F (82° - 88°C).

### Processing

To obtain optimum balance of sheet gloss and mechanical properties, the extruder profile should be set to deliver polymer at a melt temperature between 430° - 470°F (221° - 243°C). Single- or two-state screws can be used, although a two-stage screw is preferred. For two-stage screw, a first-stage compression ratio (feed depth to metering depth) of 2.5 - 2.7 and a pump ratio (second-stage metering to first-stage metering) of 1.5 - 2.0 are recommended. This is similar to an ABS screw. Die temperatures settings are between 410° - 470°F (210° - 243°C). The die should be adjusted to provide uniform polymer melt at the lips. Suggested polishing roll settings for Diamaloy GLY 7010 resin using a standard S wrap are noted below. Specific settings are dependent on sheet gauge and linear speed.

### Polishing Roll

Top  
Middle  
Bottom

### Roll Stack

160 - 210°F (71 - 93°C)  
160 - 200°F (71 - 93°C)  
150 - 190°F (66 - 88°C)

### Regrind Information

Where end-use requirements permit, up to 40% Diamaloy GLY 7010 resin regrind may be used with virgin material, during injection molding, provided that the material is kept free of contamination and is properly dried (see section on Drying). In most cases where monolayer Diamaloy GLY 7010 resin is being extruded, up to 40% Diamaloy GLY 7010 resin regrind from 100% Diamaloy GLY 7010 resin sheet or parts is generally acceptable. Where Diamaloy GLY 7010 resin is being coextruded on top of a compatible material, such as ABS, a level of 40% regrind from a mixture of Diamaloy GLY 7010 resin and substrate is generally acceptable, but in this case the regrind must go only into the substrate. Other thermoplastics, such as polystyrene, polyethylene, and polypropylene, to mention a few, are not compatible, and mixing will result in appearance and property degradation. Any regrind used must be generated from properly molded parts and/or thermoformed parts and trim scrap. All regrind used must be clean, uncontaminated, and thoroughly blended with virgin resin prior to drying and processing. Under no circumstances should degraded, discolored, or contaminated material be used for regrind. Material of this type should be discarded. Improperly mixed and/or dried resin may diminish the desired properties of Diamaloy GLY 7010 resin. It is critical that you test finished parts produced with any amount of regrind to ensure that your end-use performance requirements are fully met. Regulatory or testing organizations (e.g., UL) may have specific requirements limiting the allowable amount of regrind. Because third party regrind generally does not have a traceable heat history, nor offer any assurance that proper temperatures, conditions, and/or materials were used in processing, extreme caution must be exercised in buying and using regrind from third parties.

The use of regrind materials should be avoided entirely in those applications where resin properties equivalent to virgin material are required, including but not limited to color quality, impact strength, resin purity, and/or load-bearing performance.



DIAMOND POLYMERS, INC.

*Preliminary Data Sheet*  
 ASA Weatherable Polymers  
 Extrusion Grade

# Diamaloy GLY 7010

PROPERTIES	ASTM METHOD	UNITS ENGLISH METRIC	
<b>PHYSICAL</b>			
Melt Flow Rate- Procedure A 220°C/10 kg 260°C/ 5 kg	D-1238	g/10 min	3.7 3.5
Specific Gravity	D-792		1.06
Mold Shrinkage	D-955	%	0.4 - 0.5
Rockwell Hardness	D-785	R Scale	91
Gloss, untextured, 60°	D-523		95
<b>IMPACT</b>			
Izod Impact, notched (0.125") @ 73°F @ -22°F	D-256	ft-lb/in	9.0 2.0
Instrumented Impact Total Energy @ 73°F @ -22°F	D-3763	in-lb	214 149
<b>TENSILE</b>			
Tensile Strength @ Yield Type 1 bar, chs 2 in/min	D-638	psi MPa	6,100 42
Tensile Strength @ Break Type 1 bar, chs 2 in/min	D-638	psi MPa	5,100 35
% Elongation @ Yeild, Type 1 bar, chs 2 in/min	D-638	%	3.2
% Elongation @ Break Type 1 bar, chs 2 in/min	D-638	%	40
Tensile Modulus chs 2 in/min	D-638	psi MPa	279,000 1,922

EAP/09-03-09

The information contained herein is provided for general reference purposes only. Diamond Polymers Inc. makes no guarantee or warranty and does not assume liability with respect to the accuracy or completeness of the information presented, or the product results in any specific instance and hereby expressly disclaims any implied warranties of suitability or fitness for a particular purpose or any other warranties or representations whatsoever expressed or implied. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of patent.



DIAMOND POLYMERS, INC.

*Preliminary Data Sheet*

ASA Weatherable Polymers  
Extrusion Grade

**Diamaloy  
GLY 7010**

PROPERTIES	ASTM METHOD	UNITS ENGLISH METRIC	
<b>FLEXURAL</b>			
Flexural Modulus, 0.125 inch bar chs 0.05 in/min, 2 in span	D-790	psi MPa	279,000 1,922
Flexural Strength, 0.125" bar chs 0.05 in/min, 2 in span	D-790	psi MPa	8,700 60
<b>THERMAL</b>			
Heat Deflection Temperature 0.125" bar @ 1.8 MPa (264 psi)	D-648	°F °C	170 77
Heat Deflection Temperature 0.125" bar @ 0.455 MPa (66 psi)	D-648	°F °C	195 90
CTE, flow, -40°F to100°F CTE, xflow, -40°F to100°F	E831	1/°F	5.0 E-05 6.0 E-05
Vicat Softening Point RateB/50	D-1525	°F °C	216 102
Relative Temperature Index, Elec.	UL 746B	°C	50
Relative Temperature Index, Mech. w/impact w/o impact	UL 746B	°C	50 50
<b>ELECTRICAL</b>			
Hot Wire Ignition (PLC)	UL 746A	PLC Code	3
High Ampere Arch Ign, surface (PLC)	UL 746A	PLC Code	0
Comparative Tracking Index (UL) (PLC)	UL 746A	PLC Code	0
<b>FLAME CHARACTERISTICS</b>			
Flammability, 0.059 in	UL94 UL 746C		HB f2

EAP/09-02-09

The information contained herein is provided for general reference purposes only. Diamond Polymers Inc. makes no guarantee or warranty and does not assume liability with respect to the accuracy or completeness of the information presented, or the product results in any specific instance and hereby expressly disclaims any implied warranties of suitability or fitness for a particular purpose or any other warranties or representations whatsoever expressed or implied. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of patent.